



# Glazed bricks | pearl range

Wienerberger Code	Various
Production Plant	Panningen (Netherlands)
Manufacture	Extruded
Configuration	Perforated
Colour	Various
Appearance	Glazed/Smooth
Work Size (mm)	215 x 102.5 x 65
Pack Quantity	384
Individual Dry Brick Weight (kg)	2.4



## Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T2/R1
Gross Dry Density (kg/m <sup>3</sup> /Tolerance)	1700 (D1)
Compressive Strength (N/mm <sup>2</sup> )	≥50
Thermal Conductivity (W/(m·K)) λ <sub>10,dry,unit</sub> value (EN 1745 tabulated: S1)	P=90% 0.55
Durability Designation	F2
Water Absorption (%)	≤2
Initial Rate of Water Absorption (kg/(m <sup>2</sup> ·min))	Min. 0.0 Max. 0.5
Active Soluble Salts	S2
Reaction to Fire	Class A1

 **BIM OBJECTS** are available to download

**GET IN TOUCH**  
 ☎ 0161 491 8200  
 ✉ [wbukmarketing@wienerberger.com](mailto:wbukmarketing@wienerberger.com)  
 🌐 [wienerberger.co.uk/glazed-bricks](http://wienerberger.co.uk/glazed-bricks)

